



PERFORMANCE GUIDE

www.m3assoc.com

Version: 3

PRODUCT: MACfilm[®]

Date: 8/2004

GS - Series Strip Adhesive Approved: WEJ

PRODUCT DESCRIPTION The GS-Series of strip adhesives are made up of an unsupported SBR pressure sensitive adhesive, specially coated by MACTac using a patented, proprietary process, and wound on a 60# densified kraft release liner. *The GS Series is also available with a 2 mil polyester liner as a custom construction.*

The adhesive used in the GS-Series provides very aggressive tack and peel adhesion along with superior shear strength. This adhesive bonds to a wide variety of materials including low energy surfaces such as polyethylene and polypropylene. The standard thicknesses of 5 to 50 mils provides the mass needed to establish secure bonds to uneven or irregular surfaces.

The GS-Series strip adhesives are available in a number of narrow width sizes ranging from 1/4" to 11 1/2". The tolerance for any given width is +/- 1/16". Typically provided as a single or double strip of adhesive on the 60# liner, each roll has ungummed edges for ease of handling and quick liner removal. *There are manufacturing limitations, however, so please contact your district sales manager to review your application in order to determine suitability.*

The following properties are typical for a 20 mil thick adhesive product.

PROPERTIES TEST METHOD	Quick Tack, Lbs./sq. in.	TYPICAL VALUES* PHYSICAL
Peel Adhesion, Lbs./in.	PSTC - 3 Stainless Steel - 30 minute residence	22 +
Shear, Hours to Fail	PSTC - 7 Stainless Steel - 1000 g/sq. in. @ 72°F	300+
Thickness, inches	Adhesive only .020 or .035	

Temperature Range Guidelines

Application: Above 50°F (10°C) for best performance. End Use: 0°F to 180°F (-18°C to 82°C)

CHEMICAL RESISTANCE Resistant to water, detergent and alcohol. Not recommended for use in contact with aliphatic or aromatic hydrocarbons

SHELF LIFE

One year when stored at 75°F. (24°C.) and 50% relative humidity or less.

• Values given are typical and are not necessarily for use in specifications. Product reinforced with 2 mil PET during adhesion tests

Distributed by M-3 & Associates, Inc.

(888) 611-1041

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

TM Trademark of Morgan Adhesives Company. © Registered Trademark of Morgan Adhesives Company. www.MACTac.com

